

treadmaster Joint Sealer

Treadmaster Joint Sealer is a one-component halogen-free moisture cured gunnable sealer in convenient 290mls cartridge form, developed specifically for sealing around the edges and between the joins of sheets and tiles of treadmaster flooring.

It is available in a wide range of standard colours, or can be colour matched to customers' exact requirements.

It is a non-toxic material and does not affect the fire properties of treadmaster installations. The cured material is resistant to the effects of common contaminants and cleaning agents.

In use the sealer has a low odour and is easily applied using a standard cartridge gun. It begins to skin over after approx 20 mins and is fully cured to a depth of 2-3mm after 24hrs.

Application:

All surfaces must be clean, dry and free from oil, grease and dust.

Apply the sealer carefully along the joint and tool to a smooth finish if required using soapy solution before skin formation.

Clean equipment and excess sealer with white spirit immediately after application and before curing.

Technical Properties:

Curing System	Moisture Cure		Application Temp.	4°C to 35°C
Skin Formation*	20 mins		Cleaning	White Spirit
Curing Rate*	2-3mm / 24hrs		Tooling	Soapy solution
Hardness	40 - 45° Shore A		Shelf Life	12 months
Temp. Resistance	-40 to +90°C			
Tear Strength	2.5N/mm ²			
Elongation at Break	> 350%			

Yield per 290ml Cartridge

Bead Diameter mm	Linear Metres
2	90

OR

Bead Width mm	Linear metres per mm thickness
2	145

treadmaster
flooring

treadmaster your partner for passenger transport

Contact us at www.treadmasterflooring.com or call +44 (0)1579 321 984

No PVC

Information in this document and otherwise supplied to users is based on our general experience and is given in good faith but because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice. Statements of operating limits quoted in this document are not an indication that these values can be simultaneously applied. A safe handling data sheet on this material is available on request.



Tiflex Limited, Tiflex House,
Liskeard, PL14 4NB, UK