

Treadmaster No.10 Contact Adhesive

Multipurpose Contact Adhesive

Treadmaster No 10 is a non-flammable contact adhesive, suitable for bonding Treadmaster Transport flooring. It is a single-part polychloroprene adhesive that has good heat and water resistance and allows the user to walk on immediately after fitting.

Instructions for use:

1. Ensure surfaces to be bonded are clean, dry and free from grease, dust, and other contaminants.
2. Using a brush or scraper apply an even coat to both surfaces. The amount of adhesive required will vary according to porosity/smoothness of the substrate.
3. When the surfaces become tacky (3 - 20 minutes), lay on Treadmaster flooring and consolidate under maximum pressure to ensure a secure bond.
4. The Treadmaster flooring can be walked on immediately after assembly.
5. Full bond strength will not be achieved until 24 hours after assembly.

Base	Polychloroprene	Viscosity CPS	3000-4000 @ 20°C
Appearance	Cream	Open-Time	3-20 minutes
Temperature Resistance	-20°C to 80°C	Shelf Life	12 months
Coverage	3.5m ² /Ltr	Storage	5°C to 25°C
Application Temperature	5°C to 30°C	Environmental	Solvent/Hazardous/ Non- Flammable

Supply Details:

Supplied in a 5 litre container.

treadmaster your partner for passenger transport
Contact us at www.treadmasterflooring.com or call +44 (0)1579 320808

Information in this document and otherwise supplied to users is based on our general experiences and is given in good faith but, because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice. Statements of operating limits are quoted in this document are not an indication that these values can be simultaneously applied. A safe handling data sheet on this material is available on request.

Tiflex
Tiflex Limited, Tiflex House,
Liskeard, PL14 4NB UK

treadmaster
flooring

PVC Free

02/11/2016
DL - Revision 1