

TM5

Technical Data

Fire properties

Property	Test Method	Typical Properties
Surface spread of flame	BS476-7	Class 2
Smoke density (A_0 max)	BS6853 D.8.6	53
Toxicity of combustion	BS6853 annex B	R < 2
BS6853 PCTV category		1b
Reaction to fire	NFF 16-101/102	F1 M2
Gross calorific potential	ISO 1716	18.7 MJ/kg

Physical properties

Property	Test Method	Typical Properties
Sheet Size (max)	Width / Length	1.20 x 10m
Hardness, °IRHD	ISO 48	92°
Density, g/cm ³	ISO 2781	1.55
Tensile Strength, MPa	ASTM F152	4.0
Flexibility	ASTM F147	3d
Abrasion Resistance	Taber Abrader 3000 cycles, 500g	Weight loss 0.5g Thickness loss 0.12mm
Slip Resistance	TRRL Pendulum	Dry 100 Wet 30
Residual Indentation	BS 6826	1%

treadmaster
flooring

treadmaster your partner for passenger transport

Contact us at www.treadmasterflooring.com or call +44 (0)1579 321 984

No PVC

Information in this document and otherwise supplied to users is based on our general experience and is given in good faith but because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice. Statements of operating limits quoted in this document are not an indication that these values can be simultaneously applied. A safe handling data sheet on this material is available on request.

Tiflex

Tiflex Limited, Tiflex House,
Liskeard, PL14 4NB, UK

Revision 3
06/12/2017